

12-22-99

A

UTILITY PATENT APPLICATION TRANSMITTAL (Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.
10208-1Total Pages in this Submission
40**TO THE ASSISTANT COMMISSIONER FOR PATENTS**Box Patent Application
Washington, D.C. 20231

Transmitted herewith for filing under 35 U.S.C. 111(a) and 37 C.F.R. 1.53(b) is a new utility patent application for an invention entitled:

A CATALYTIC CRACKING PROCESS USING A MODIFIED MESOPOROUS ALUMINOPHOSPHATE MATERIAL

and invented by:

Arthur W. Chester; Frederick E. Daugherty; Anthony S. Fung; Charles T. Kresge; HyeKyung C. Timken;
James C. Vartuli; Ranjit Kumar; Terry G. Roberie; Michael S. Ziebarthjc530 U.S. PTO
09/468450
12/21/99If a **CONTINUATION APPLICATION**, check appropriate box and supply the requisite information:☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: _____

Which is a:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: _____

Which is a:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: _____

Enclosed are:

Application Elements

1. ☒ Filing fee as calculated and transmitted as described below
2. ☒ Specification having 36 pages and including the following:
 - a. ☒ Descriptive Title of the Invention
 - b. ☐ Cross References to Related Applications (if applicable)
 - c. ☐ Statement Regarding Federally-sponsored Research/Development (if applicable)
 - d. ☐ Reference to Microfiche Appendix (if applicable)
 - e. ☒ Background of the Invention
 - f. ☒ Brief Summary of the Invention
 - g. ☒ Brief Description of the Drawings (if drawings filed)
 - h. ☒ Detailed Description
 - i. ☒ Claim(s) as Classified Below
 - j. ☒ Abstract of the Disclosure

UTILITY PATENT APPLICATION TRANSMITTAL
(Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.

10208-1

Total Pages in this Submission

40

Application Elements (Continued)

3. ☒ Drawing(s) *(when necessary as prescribed by 35 USC 113)*
- a. ☐ Formal Number of Sheets 1
- b. ☐ Informal Number of Sheets _____
4. ☐ Oath or Declaration
- a. ☐ Newly executed *(original or copy)* ☐ Unexecuted
- b. ☐ Copy from a prior application (37 CFR 1.63(d)) *(for continuation/divisional application only)*
- c. ☐ With Power of Attorney ☐ Without Power of Attorney
- d. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application,
see 37 C.F.R. 1.63(d)(2) and 1.33(b).
5. ☐ Incorporation By Reference *(usable if Box 4b is checked)*
The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied
under Box 4b, is considered as being part of the disclosure of the accompanying application and is hereby
incorporated by reference therein.
6. ☐ Computer Program in Microfiche *(Appendix)*
7. ☐ Nucleotide and/or Amino Acid Sequence Submission *(if applicable, all must be included)*
- a. ☐ Paper Copy
- b. ☐ Computer Readable Copy *(identical to computer copy)*
- c. ☐ Statement Verifying Identical Paper and Computer Readable Copy

Accompanying Application Parts

8. ☐ Assignment Papers *(cover sheet & document(s))*
9. ☐ 37 CFR 3.73(B) Statement *(when there is an assignee)*
10. ☐ English Translation Document *(if applicable)*
11. ☐ Information Disclosure Statement/PTO-1449 ☐ Copies of IDS Citations
12. ☐ Preliminary Amendment
13. ☒ Acknowledgment postcard
14. ☒ Certificate of Mailing
- ☐ First Class ☒ Express Mail *(Specify Label No.):* EE691514962US

UTILITY PATENT APPLICATION TRANSMITTAL (Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.
10208-1

Total Pages in this Submission
40

Accompanying Application Parts (Continued)

15. ☐ Certified Copy of Priority Document(s) (if foreign priority is claimed)


16. ☐ Additional Enclosures (please identify below):

Fee Calculation and Transmittal

CLAIMS AS FILED

For	#Filed	#Allowed	#Extra	Rate	Fee
Total Claims	9	- 20 =	0	x \$18.00	\$0.00
Indep. Claims	1	- 3 =	0	x \$78.00	\$0.00
Multiple Dependent Claims (check if applicable) <input type="checkbox"/>					\$0.00
BASIC FEE					\$760.00
OTHER FEE (specify purpose) _____					\$0.00
TOTAL FILING FEE					\$760.00

- ☐ A check in the amount of _____ to cover the filing fee is enclosed.
- ☒ The Commissioner is hereby authorized to charge and credit Deposit Account No. **19-3150** as described below. A duplicate copy of this sheet is enclosed.
- ☒ Charge the amount of **\$760.00** as filing fee.
 - ☒ Credit any overpayment.
 - ☒ Charge any additional filing fees required under 37 C.F.R. 1.16 and 1.17.
 - ☐ Charge the issue fee set in 37 C.F.R. 1.18 at the mailing of the Notice of Allowance pursuant to 37 C.F.R. 1.311(b).


Signature

Peter W. Roberts
Attorney for the Applicants
Registration Number 31,702
(703) 846-7732

Dated: December 21, 1999

CC:

Mobil Oil Corporation
3225 Gallows Road
Fairfax, VA 22037

A CATALYTIC CRACKING PROCESS USING A MODIFIED MESOPOROUS ALUMINOPHOSPHATE MATERIAL

BACKGROUND OF THE INVENTION

A. Field of the Invention

This invention relates to a catalytic cracking process using a mesoporous aluminophosphate material modified with at least one element selected from zirconium, cerium, lanthanum, manganese, cobalt, zinc, and vanadium. Such materials have high surface area and excellent thermal and hydrothermal stability, with a relatively narrow pore size distribution in the mesoporous range.

B. Description of the Prior Art

Amorphous metallophosphates are known and have been prepared by various techniques. One such material is described in U.S. Patent No. 4,767,733. This patent describes rare earth aluminum phosphate materials, which, after calcination, have a relatively broad pore size distribution with a large percentage of pores greater than 150 Å. The typical pore size distribution is as follows:

<u>Pore Size</u>	<u>Volume Percent</u>
50 to 100 Å	5 to 20 %
100 to 150 Å	10 to 35 %
150 to 200 Å	15 to 50 %
200 to 400 Å	10 to 50 %

U.S. Patent Nos. 4,743,572 and 4,834,869 describe magnesia-alumina-aluminum phosphate support materials prepared using organic cations (e.g., tertiary or tetraalkylammonium or phosphonium cations) to control the pore size distribution. When organic cations are used in the synthesis, the resulting materials have a narrow pore size distribution in the range from 30 to 100 Å. When they are not used, the pore size is predominantly greater than 200 Å. U.S. Patent No. 4,179,358 also describes magnesium-alumina-aluminum phosphate materials, materials described as having excellent thermal stability.

5 The use of aluminophosphates in cracking catalysts is known. For example, U.S. Patent No. 4,919,787 describes the use of porous, rare earth oxide, alumina, and aluminum phosphate precipitates for catalytic cracking. This material was used as part of a cracking catalyst, where it acted as a metal passivating agent. The use of a magnesia-alumina-aluminum phosphate supported catalyst for cracking gasoline feedstock is
10 described in U.S. Patent No. 4,179,358. Additionally, a process for catalytic cracking high-metals-content-charge stocks using an alumina-aluminum phosphate-silica-zeolite catalyst is described in U.S. Patent No. 4,158,621.

 There remains a need in the art for highly stable aluminophosphate materials for use in catalytic cracking processes, as well as for simple, safe processes for producing
15 these materials. The aluminophosphate materials preferably possess excellent hydrothermal and acid stability with uniform pore sizes in the mesoporous range, and provide increased gasoline yields with increased butylene selectivity in C₄ gas.

SUMMARY OF THE INVENTION

20 This invention resides in a process for catalytic cracking of a hydrocarbon feedstock comprising contacting the feedstock with a catalyst composition comprising a mesoporous aluminophosphate material which comprises a solid aluminophosphate composition modified with at least one element selected from zirconium, cerium, lanthanum, manganese, cobalt, zinc, and vanadium, wherein the mesoporous
25 aluminophosphate material has a specific surface of at least 100 m²/g, an average pore diameter less than or equal to 100 Å, and a pore size distribution such that at least 50% of the pores have a pore diameter less than 100 Å.

 Preferably, the mesoporous aluminophosphate material has an average pore diameter of 30 to 100 Å.

30 Preferably, the catalyst composition also comprises a primary catalytically active cracking component.

 Preferably, the primary catalytically active cracking component comprises a large pore molecular sieve having a pore size greater than about 7 Angstrom.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a process for converting feedstock hydrocarbon compounds to product hydrocarbon compounds of lower molecular weight than the feedstock hydrocarbon compounds. In particular, the present invention provides a process for catalytically cracking a hydrocarbon feed to a mixture of products comprising gasoline and distillate, in which the gasoline yield is increased and the sulfur content of the gasoline and distillate is reduced. Catalytic cracking units which are amenable to the process of the invention operate at temperatures from about 200°C to about 870°C and under reduced, atmospheric or superatmospheric pressure. The catalytic process can be either fixed bed, moving bed or fluidized bed and the hydrocarbon flow may be either concurrent or countercurrent to the catalyst flow. The process of the invention is particularly applicable to the Fluid Catalytic Cracking (FCC) or Thermoform Catalytic Cracking (TCC) processes.

The TCC process is a moving bed process and uses a catalyst in the shape of pellets or beads having an average particle size of about one-sixty-fourth to one-fourth inch. Active, hot catalyst beads progress downwardly cocurrent with a hydrocarbon charge stock through a cracking reaction zone. The hydrocarbon products are separated from the coked catalyst and recovered, and the catalyst is recovered at the lower end of the zone and regenerated. Typically TCC conversion conditions include an average reactor temperature of about 450°C to about 510°C; catalyst/oil volume ratio of about 2 to about 7; reactor space velocity of about 1 to about 2.5 vol./hr./vol.; and recycle to fresh feed ratio of 0 to about 0.5 (volume).

The process of the invention is particularly applicable to fluid catalytic cracking (FCC), which uses a cracking catalyst which is typically a fine powder with a particle size of about 10 to 200 microns. This powder is generally suspended in the feed and propelled upward in a reaction zone. A relatively heavy hydrocarbon feedstock, e.g., a gas oil, is admixed with the cracking catalyst to provide a fluidized suspension and cracked in an elongated reactor, or riser, at elevated temperatures to provide a mixture of lighter hydrocarbon products. The gaseous reaction products and spent catalyst are discharged from the riser into a separator, e.g., a cyclone unit, located within the upper section of an enclosed stripping vessel, or stripper, with the reaction products being conveyed to a

5 product recovery zone and the spent catalyst entering a dense catalyst bed within the lower section of the stripper. In order to remove entrained hydrocarbons from the spent catalyst prior to conveying the latter to a catalyst regenerator unit, an inert stripping gas, e.g., steam, is passed through the catalyst bed where it desorbs such hydrocarbons conveying them to the product recovery zone. The fluidizable catalyst is continuously
10 circulated between the riser and the regenerator and serves to transfer heat from the latter to the former thereby supplying the thermal needs of the cracking reaction which is endothermic.

Typically, FCC conversion conditions include a riser top temperature of about 500°C to about 595°C, preferably from about 520°C to about 565°C, and most preferably
15 from about 530°C to about 550°C; catalyst/oil weight ratio of about 3 to about 12, preferably about 4 to about 11, and most preferably about 5 to about 10; and catalyst residence time of about 0.5 to about 15 seconds, preferably about 1 to about 10 seconds.

The hydrocarbon feedstock to be cracked may include, in whole or in part, a gas oil (e.g., light, medium, or heavy gas oil) having an initial boiling point above 204°C, a 50
20 % point of at least 260°C and an end point of at least 315°C. The feedstock may also include vacuum gas oils, thermal oils, residual oils, cycle stocks, whole top crudes, tar sand oils, shale oils, synthetic fuels, heavy hydrocarbon fractions derived from the destructive hydrogenation of coal, tar, pitches, asphalts, hydrotreated feedstocks derived from any of the foregoing, and the like. As will be recognized, the distillation of higher
25 boiling petroleum fractions above about 400°C must be carried out under vacuum in order to avoid thermal cracking. The boiling temperatures utilized herein are expressed for convenience in terms of the boiling point corrected to atmospheric pressure. Resids or deeper cut gas oils with high metals contents can also be cracked using the process of the invention.

30 The process of the invention uses a catalyst composition comprising a mesoporous aluminophosphate material modified with at least one element selected from zirconium, cerium, lanthanum, manganese, cobalt, zinc, and vanadium. "Mesoporous," as used in this patent application, means a material having pores with diameters in the approximate range 30-100 Å.

Various important properties of the aluminophosphate materials used in the process of the invention have been identified. In particular, the materials should have a specific surface area of at least 100 m²/g, preferably at least 125 m²/g, and most advantageously at least 175 m²/g. Additionally, the materials should have an average pore diameter less than or equal to 100 Å, preferably less than 80 Å, and most advantageously less than 60 Å.

Pore size distribution and pore volume provide other measures of the porosity of a material. In the modified aluminophosphate materials used in this invention, 50% or more of the pores have a diameter less than 100 Å, more preferably 60% or more of the pores have a diameter less than 100 Å, and most preferably, 80% or more of the pores have a diameter less than 100 Å. With respect to the pore volume, the aluminophosphate materials used in the process of the invention preferably have a pore volume in the range from 0.10 cc/g to 0.75 cc/g, and more preferably within the range of 0.20 to 0.60 cc/g.

The mesoporous aluminophosphate materials used in the process of the invention are synthesized using inorganic reactants, water and aqueous solutions and in the absence of organic reagents or solvents. This feature simplifies production and waste disposal. Synthesis involves providing an aqueous solution that contains a phosphorus component (e.g., phosphoric acid, phosphate salts such as ammonium phosphate which can be monobasic, dibasic or tribasic salt); an inorganic aluminum containing component (e.g., sodium aluminate, aluminum sulfate, or combinations of these materials); and an inorganic modifying component containing at least one element selected from zirconium, cerium, lanthanum, iron, manganese, cobalt, zinc, and vanadium. Typically, the molar ratios of the starting materials are as follows:

<u>Component</u>	<u>Useful</u>	<u>Preferred</u>
Phosphorus component	0.02-0.90	0.05-0.85
Aluminum containing component	0.02-0.90	0.05-0.85
Inorganic modifying component	0.01-0.50	0.02-0.40

After thoroughly mixing the ingredients, the pH of the aqueous solution is adjusted, with an acid or base, into the range of about 7 to about 12 so that a solid

material (e.g., a homogeneous gel) forms in and precipitates from the solution. After pH adjustment, the aqueous solution may be exposed to hydrothermal or thermal treatment at about 100°C to about 200°C to further facilitate uniform pore formation. After formation, the solid material, which includes the desired aluminophosphate material, can be recovered by any suitable method known in the art, e.g., by filtration. The filtered cake is then washed with water to remove any trapped salt, and then may be contacted with a solution containing ammonium salt or acid to exchange out the sodium ions. Such reduction in the sodium level of is found to increase the hydrothermal stability of the aluminophosphate material. Typically, the sodium level of the final aluminophosphate material should be less than 1.0 wt% Na. After washing and optional exchange, the solid material is dried and calcined.

Although any suitable inorganic modifying component can be used in synthesizing the mesoporous aluminophosphate materials used in the process of the invention, preferably it is a sulfate or a nitrate of zirconium, cerium, lanthanum, manganese, cobalt, zinc, or vanadium.

In the process of the invention, the modified aluminophosphate material is used in the cracking catalyst, preferably as a support in combination with a primary cracking catalyst component and an activated matrix. Other conventional cracking catalyst materials, such as additive catalysts, binding agents, clays, alumina, silica-alumina, and the like, can also be included as part of the cracking catalyst. Typically, the weight ratio of the modified aluminophosphate material to the primary cracking catalyst component is about 0.01 to 0.5, preferably 0.02 to 0.15.

The primary cracking component may be any conventional large-pore molecular sieve having cracking activity and a pore size greater than about 7 Angstrom including zeolite X (U.S. Patent 2,882,442); REX; zeolite Y (U.S. Patent 3,130,007); Ultrastable Y zeolite (USY) (U.S. Patent 3,449,070); Rare Earth exchanged Y (REY) (U.S. Patent 4,415,438); Rare Earth exchanged USY (REUSY); Dealuminated Y (DeAl Y) (U.S. Patent 3,442,792; U.S. Patent 4,331,694); Ultrahydrophobic Y (UHPY) (U.S. Patent 4,401,556); and/or dealuminated silicon-enriched zeolites, e.g., LZ-210 (U.S. Patent 4,678,765). Preferred are higher silica forms of zeolite Y. Zeolite ZK-5 (U.S. Patent 3,247,195);, zeolite ZK-4 (U.S. Patent 3,314,752); ZSM-20 (U.S. Patent 3,972,983);

5 zeolite Beta (U.S. Patent 3,308,069) and zeolite L (U.S. Patents 3,216,789; and
4,701,315). Naturally occurring zeolites such as faujasite, mordenite and the like may also
be used. These materials may be subjected to conventional treatments, such as
impregnation or ion exchange with rare earths to increase stability. The preferred large
pore molecular sieve of those listed above is a zeolite Y, more preferably an REY, USY or
10 REUSY.

Other suitable large-pore crystalline molecular sieves include pillared silicates
and/or clays; aluminophosphates, e.g., ALPO4-5, ALPO4-8, VPI-5;
silicoaluminophosphates, e.g., SAPO-5, SAPO-37, SAPO-31, SAPO-40; and other metal
aluminophosphates. These are variously described in U.S. Patents 4,310,440; 4,440,871;
15 4,554,143; 4,567,029; 4,666,875; 4,742,033; 4,880,611; 4,859,314; and 4,791,083.

The cracking catalyst may also include an additive catalyst in the form of a medium
pore zeolite having a Constraint Index (which is defined in U.S. Patent No. 4,016,218) of
about 1 to about 12. Suitable medium pore zeolites include ZSM-5 (U.S. Patent
3,702,886 and Re. 29,948); ZSM-11 (U.S. Patent 3,709,979); ZSM-12 (U.S. Patent
20 4,832,449); ZSM-22 (U.S. Patent 4,556,477); ZSM-23 (U.S. Patent 4,076,842); ZSM-35
(U.S. Patent 4,016,245); ZSM-48 (U.S. Patent 4,397,827); ZSM-57 (U.S. Patent
4,046,685); PSH-3 (U.S. Patent 4,439,409); and MCM-22 (U.S. Patent 4,954,325) either
alone or in combination. Preferably, the medium pore zeolite is ZSM-5.

The invention will now be more particularly described with reference to the
25 following Examples. In the Examples, pore size distributions are measured by a N₂
desorption process based on ASTM method D4641 and pore volumes are measured by a
N₂ adsorption process based on ASTM method D4222, which documents are entirely
incorporated herein by reference. The pore volume and pore size distribution data
reported herein correspond to pores ranging from approximately 14 to 1000 Å in radius,
30 and do not include any microporous pores which have typically less than 14 Å in radius.

EXAMPLE 1 - Zirconium Aluminophosphate

A. Production of the Support Material

A zirconium modified aluminophosphate material was prepared by mixing
35 together, at 40° C, 1700 grams of water, 29 grams of concentrated phosphoric acid, 133

5 grams of zirconium sulfate, and 170 grams of sodium aluminate. In this mixture, the zirconium/aluminum/phosphorus molar ratio was 0.35/0.5/0.15. After thoroughly mixing these ingredients, the pH of the solution was adjusted to 11 using ammonium hydroxide. The resulting mixture was transferred to a polypropylene bottle and placed in a steam box (100° C) for 48 hours. The mixture was then filtered to separate the solid material from
 10 the liquid, and the solid material was washed to provide a wet cake, a portion of which was dried at about 85° C (another portion of this washed material was used in the following test for measuring its hydrothermal stability). A portion of the dried solid material was calcined in air at 540° C for six hours. The resulting zirconium aluminophosphate material had the following properties and characteristics:

15

<u>Elemental Analysis</u>	<u>Weight Percent</u>
Zr	26.4
Al	24.3
P	4.0

20

Surface Area - 175 m²/g
 Average pore diameter - 41 Å
 Pore volume - 0.21 cc/g

25

<u>Pore Size Distribution</u>	<u>Desorption, %</u>
< 50 Å	80%
50 - 100 Å	10%
100 - 150 Å	5%
> 150 Å	5%.

30

B. Hydrothermal Stability Test

A portion of the wet cake from Example 1A above was slurried with deionized (DI) water (20 g DI water per g of ZrAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The resultant material was dried
 35 at 120° C overnight and then air calcined at 540° C for three hours. One portion of this

- 5 calcined material was steamed (100% atmospheric pressure steam) at 815° C for 2 hours, and another portion was steamed at 815° C for 4 hours. The surface area of the calcined and steamed materials were as follows:

	<u>Material</u>	<u>Surface Area, m²/g</u>
10	Calcined only	227
	Steamed for 2 hours	85
	Steamed for 4 hours	68

- These results demonstrate that the zirconium aluminophosphate material according to the invention is hydrothermally stable and maintains about 30% or more of its surface area under the severe steam deactivating conditions, such as would be experienced in a FCC regenerator. It will also be seen that sodium removal resulting from the acid exchange increased the surface area of the base air calcined material from 175 m²/g for the product of Example 1A to 227 m²/g for the product of Example 1B.

20 **EXAMPLE 2 - Cerium Aluminophosphate**

A. Production of the Support Material

- A cerium modified aluminophosphate material was prepared by mixing together, at 40° C, 2100 grams of water, 45 grams of concentrated phosphoric acid, 133 grams of cerium sulfate, 75 grams of concentrated sulfuric acid, and 760 grams of sodium aluminate. In this mixture, the cerium/aluminum/phosphorus molar ratio was 1/8/1. After thoroughly mixing these ingredients, the pH of the solution was adjusted to 7 using 50% sulfuric acid. The resulting mixture was transferred to a polypropylene bottle and placed in a steam box (100° C) for 48 hours. The mixture was then filtered to separate the solid material from the liquid, and the solid material was washed to provide a wet cake, a portion of which was dried at about 85° C (another portion of this washed material was used in the following hydrothermal stability test). A portion of this solid material was calcined in air at 540° C for six hours. The resulting cerium aluminophosphate material had the following properties and characteristics:

5	<u>Elemental Analysis</u>	<u>Weight Percent</u>
	Ce	8.6
	Al	36.2
	P	1.6

Surface Area - 272 m²/g

10 Average pore diameter - 65 Å

Pore volume - 0.50 cc/g

	<u>Pore Size Distribution</u>	<u>Desorption, %</u>
	< 50 Å	44%
15	50 - 100 Å	20%
	100 - 150 Å	12%
	> 150 Å	24%.

B. Hydrothermal Stability Test

20 A portion of the wet cake from Example 2A above was slurried with deionized (DI) water (20 g DI water per g of CeAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The resultant material was dried at 120° C overnight and then air calcined at 540° C for three hours. One portion of this
25 calcined material was steamed (100% atmospheric pressure steam) at 815° C for 2 hours, and another portion was steamed at 815° C for 4 hours. The surface area of these calcined and steamed materials were as follows:

	<u>Material</u>	<u>Surface Area, m²/g</u>
30	Calcined only	272
	Steamed for 2 hours	138
	Steamed for 4 hours	143

These results demonstrate that the cerium aluminophosphate material according to the invention is hydrothermally stable and maintains greater than 50% of its surface area under
35 these severe steam deactivating conditions.

5

EXAMPLE 3 - Cerium Aluminophosphate

Another cerium modified aluminophosphate material was prepared by mixing together, at 40° C, 2100 grams of water, 360 grams of concentrated phosphoric acid, 135 grams of cerium sulfate, and 100 grams of aluminum sulfate. In this mixture, the cerium/aluminum/phosphorus molar ratio was 1/1/8. After thoroughly mixing these ingredients, the pH of the solution was adjusted to 7 using ammonium hydroxide. The resulting mixture was transferred to a polypropylene bottle and placed in a steam box (100° C) for 48 hours. The mixture was then filtered to separate the solid material from the liquid, and the solid material was washed and dried at about 85° C. This solid material was calcined in air at 540° C for six hours. The resulting cerium aluminophosphate material had the following properties and characteristics:

<u>Elemental Analysis</u>	<u>Weight Percent</u>
Ce	31.4
Al	5.5
P	21.0
Surface Area - 133 m ² /g	
Average pore diameter - 93 Å	
Pore volume - 0.31 cc/g	
<u>Pore Size Distribution</u>	<u>Desorption, %</u>
< 50 Å	33%
50 - 100 Å	18%
100 - 150 Å	12%
> 150 Å	27%.

EXAMPLE 4 - Lanthanum Aluminophosphate

A lanthanum modified aluminophosphate material was prepared as follows. A first solution was prepared by mixing together 2500 grams of water, 90 grams of concentrated phosphoric acid, and 260 grams of lanthanum nitrate. A second solution was prepared by

5 combining 1670 grams of water and 600 grams of sodium aluminate. These two solutions were combined with stirring. The lanthanum/aluminum/phosphorus molar ratio of this mixture was 1/8/1. After thoroughly mixing these solutions, the pH of the resulting mixture was adjusted to 12 by adding 150 grams of sulfuric acid. The resulting mixture was then transferred to a polypropylene bottle and placed in a steam box (100° C) for 48
 10 hours. Thereafter, the mixture was filtered to separate the solid material from the liquid, and the solid material was washed and dried at about 85° C. This solid material was calcined in air at 540° C for six hours. The resulting lanthanum aluminophosphate material had the following properties and characteristics:

15	<u>Elemental Analysis</u>	<u>Weight Percent</u>
	La	16.6
	Al	29.8
	P	4.8
	Surface Area - 123 m ² /g	
20	Average pore diameter - 84 Å	
	Pore volume - 0.26 cc/g	
	<u>Pore Size Distribution</u>	<u>Desorption, %</u>
	< 50 Å	32%
	50 - 100 Å	56%
25	100 - 150 Å	10%
	> 150 Å	< 5%.

EXAMPLE 5 - Manganese Aluminophosphate

A manganese modified aluminophosphate material was prepared by mixing
 30 together 2100 grams of water, 45 grams of concentrated phosphoric acid, 68 grams of manganese sulfate, and 760 grams of aluminum sulfate. In this mixture, the manganese/aluminum/phosphorus molar ratio was 1/8/1. After thoroughly mixing these ingredients, the pH of the solution was adjusted to 11 by adding ammonium hydroxide. The resulting mixture was transferred to a polypropylene bottle and placed in a steam box
 35 (100° C) for 48 hours. The mixture was then filtered to separate the solid material from

the liquid, and the solid material was washed and dried at about 85°C. The solid material was re-slurried with deionized water (20 cc of DI water/g of MnAlPO_x) and the pH of the slurry was adjusted to 4.0 or slightly below with a concentrated HCl solution. The pH was maintained for 15 minutes and filtered to separate the solid material from the liquid. The filter cake was washed thoroughly with 70°C DI water until the washed solution is free of chloride anion, dried overnight at 120 °C, and then calcined in air at 540°C for six hours. The resulting manganese aluminophosphate material had the properties and characteristics listed in Table 1.

EXAMPLE 6 - Zinc Aluminophosphate

A zinc modified aluminophosphate material was prepared by mixing together 2100 grams of water, 45 grams of concentrated phosphoric acid, 115 grams of zinc sulfate, 75 grams of concentrated sulfuric acid, and 760 grams of sodium aluminate. In this mixture, the zinc/aluminum/phosphorus molar ratio was 1/8/1. After thoroughly mixing these ingredients, the pH of the solution was adjusted to 11 by adding 50% sulfuric acid. The resulting mixture was transferred to a polypropylene bottle and placed in a steam box (100° C) for 48 hours. The mixture was then filtered to separate the solid material from the liquid, and the solid material was washed and dried at about 85°C. The solid material was re-slurried with deionized water (20 cc of DI water/g of ZnAlPO_x) and the pH of the slurry was adjusted to 4.0 or slightly below with a concentrated HCl solution. The pH was maintained for 15 minutes and filtered to separate the solid material from the liquid. The filter cake was washed thoroughly with 70°C DI water, dried overnight at 120 °C, and then calcined in air at 540°C for six hours. The resulting zinc aluminophosphate material had the properties and characteristics listed in Table 1.

EXAMPLE 7 (Comparative)- Iron Aluminophosphate

A solution was prepared by mixing 1700 grams of water, 65 grams of concentrated phosphoric acid, 200 grams of ferrous sulfate, and 110 grams of aluminum sulfate. The molar ratio of the iron/aluminum/phosphorous was 0.34/0.33/0.33. The pH of the product was adjusted to 7 with the addition of concentrated ammonium hydroxide. The material was then filtered and washed and dried at ~85°C. A portion of the material was

- 5 air calcined to 540°C for six hours. The resulting iron aluminophosphate material had the properties and characteristics listed in Table 1.

Table 1

	<u>ZnAlPO_x</u> <u>Example 5</u> <u>Invention</u>	<u>MnAlPO_x</u> <u>Example 6</u> <u>Invention</u>	<u>FeAlPO_x</u> <u>Example 7</u> <u>Comparative</u>
<u>Calcined Acid Form</u>			
Metal loading, wt%	4.2% Zn	5.7% Mn	21% Fe
Al ₂ O ₃ , wt%	-	-	12.2
P, wt%	-	-	12.4
Na, wt%	0.22	0.08	0.009
Surface area, m ² /g	314	244	109
Average pore diameter (Å)	50	44	202
Pore volume (>14Å), cc/g	0.37	0.26	0.55
Pore size distribution, %			
<50 Å	39	75	4
50-100 Å	17	23	12
100-150 Å	9	1	15
>150 Å	35	1	69
<u>Steam Deactivated Catalyst</u> <u>(1500 °F for 4 hrs)</u>			
Surface area, m ² /g	155	103	6

10 The results in Table 1 show that ZnAlPO_x and MnAlPO_x of the invention retained a surface area in excess of 100 m²/g after severe steaming. However, the FeAlPO_x with a pore size distribution outside the invention lost almost all of its surface area upon steaming.

15 **EXAMPLE 8 - Cobalt Aluminophosphate**

Sample A (Invention)

A solution was prepared by mixing 500 grams of water, 45 grams of concentrated phosphoric acid, 117 grams of cobalt nitrate and 75 grams of concentrated sulfuric acid.

- 20 Another solution was prepared containing 1600 grams of water and 300 grams of sodium aluminate. These two solutions were combined with stirring. The molar ratio of the

- 5 cobalt/aluminum/phosphorous was 1/8/1. The pH of the mixture was adjusted to 9 with the addition of 50% solution of sulfuric acid. The resulting mixture was placed in a polypropylene bottle and put in a steam box (100°C) for 48 hours. The mixture was then filtered and the solid residue was washed and dried at ~85°C. A portion of the residue was air calcined to 540°C for six hours. The elemental analyses and physical properties
- 10 were as follows:

Element, wt%	
Co	7.1
Al	25.3
P	3.4
Surface Area, m ² /g	145

- A portion of the above material was exchanged four times with a 0.1N solution of ammonium nitrate and the resulting material was then filtered and washed and dried at
- 15 ~85°C. A portion of the material was air calcined to 540°C for six hours. The resulting cobalt aluminophosphate material had the properties and characteristics listed in Table 2.

Sample B (Invention)

- A solution was prepared by mixing 2100 grams of water, 45 grams of concentrated
- 20 phosphoric acid, 117 grams of cobalt nitrate, 75 grams of concentrated sulfuric acid, and 300 grams of sodium aluminate. The molar ratio of the cobalt/aluminum/phosphorous was 1/8/1. The pH of the mixture was adjusted to 8 with the addition of 50% solution of sulfuric acid. The resulting mixture was placed in a polypropylene bottle and put in a steam box (100°C) for 48 hours. The mixture was then filtered and the solid residue was
- 25 washed and dried at ~85°C. A portion of the residue was air calcined to 540°C for six hours. The elemental analyses and physical properties were as follows:

Element, wt%	
Co	6.0
Al	19.2
P	2.6
Surface Area, m ² /g	114

5 A portion of the above material was exchanged four times with a 0.1N solution of ammonium nitrate and the resulting material was then filtered and washed and dried at ~85°C. A portion of the material was air calcined to 540°C for six hours. The resulting cobalt aluminophosphate material had the properties and characteristics listed in Table 2.

10 Sample C (Invention)

A cobalt modified aluminophosphate material was prepared in the same manner as for Sample B above, except the pH of the mixture was adjusted to 7 with the addition of 50% solution of sulfuric acid. The elemental analyses and physical properties of the
15 product were as follows:

Element, wt%	
Co	6.8
Al	19.6
P	2.9

A portion of the above material was slurried with DI water (20 g DI water per g of CoAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution
20 while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The gel was dried at 120°C for overnight and calcined in air at 538°C for 3 hours. The resulting cobalt aluminophosphate material had the properties and characteristics listed in Table 2.

25 Sample D (Comparative)

A cobalt modified aluminophosphate material was prepared by mixing 2100 grams of water, 45 grams of concentrated phosphoric acid, 117 grams of cobalt nitrate, 75 grams of concentrated sulfuric acid, and 300 grams of aluminum sulfate. The molar ratio of the cobalt/aluminum/phosphorous was 1/8/1. The pH of the mixture was adjusted to
30 11 with the addition of concentrated ammonium hydroxide. The resulting mixture was placed in a polypropylene bottle and put in a steam box (100°C) for 48 hours. The mixture was then filtered and the solid residue was washed and dried at ~85°C. A portion

- 5 of the residue was air calcined to 540°C for six hours. The elemental analyses and physical properties were as follows:

Element, wt%	
Co	10.7
Al	27.4
P	5.8

- 10 A portion of the above material was slurried with DI water (20 g DI water per g of CoAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The gel was dried at 120°C for overnight and calcined in air at 538°C for 3 hours. The resulting cobalt aluminophosphate material had the properties and characteristics listed in Table 2.

15 Sample E (Comparative)

- A cobalt modified aluminophosphate material was prepared from a solution which was prepared with mixing, containing 1700 grams of water, 29 grams of concentrated phosphoric acid, 213 grams of cobalt nitrate, and 170 grams of aluminum sulfate. The molar ratio of the cobalt/aluminum/phosphorous was 0.35/0.5/0.15. The pH of the mixture was adjusted to 7 with the addition of concentrated ammonium hydroxide. The resulting mixture was placed in a polypropylene bottle and put in a steam box (100°C) for 48 hours. The mixture was then filtered and the solid residue was washed and dried at ~85°C. A portion of the residue was air calcined to 540°C for six hours. The elemental analyses and physical properties were as follows:

Element, wt%	
Co	28
Al	10.9
P	6.3

A portion of the above material was slurried with DI water (20 g DI water per g of CoAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution

- 5 while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The gel was dried at 120°C for overnight and calcined in air at 538°C for 3 hours. The resulting cobalt aluminophosphate material had the properties and characteristics listed in Table 2.

10 Hydrothermal Stability Test of the CoAlPO_x Samples

- The hydrothermal stability of each CoAlPO_x gel was evaluated by steaming the material at 1500°F (815°C) for 4 hours with 100% steam at atmospheric pressure. The results are given in Table 2 below and Figure 1. The results show that Samples A-C, with the average pore size and pore size distribution according to the invention, exhibited
- 15 excellent hydrothermal stability in that they maintained over 100 m²/g surface area even after severe steaming. In contrast, Samples D and E, without the narrowly-defined mesopores structure of the invention, lost nearly all of their surface area upon steaming at 1500°F.

20

Table 2

Sample	A	B	C	D	E
Calcined Acid Form					
Co loading, wt%	6.2	7.9	10	15	28
Al ₂ O ₃ , wt%	47.8	36	51	18	20
P, wt%	3.4	2.6	4	11	10
Na, wt%	0.49	0.28	0.05	0.01	0.01
Surface area, m ² /g	321	247	175	103	82
Average pore diameter (Å)	67	74	74	152	108
Pore volume (>14Å), cc/g	0.55	0.44	0.37	0.38	0.24
Pore size distribution, %					
<50 Å	38	29	32	8	13
50-100 Å	32	39	27	14	27
100-150 Å	9	11	13	14	19
>150 Å	21	21	28	64	41
Steam Deactivated Catalyst (1500°F for 4 hrs)					
Surface area, m ² /g	128	113	111	29	18

5 **EXAMPLE 9 -Vanadium Aluminophosphate**

Sample F

A solution was prepared by mixing 2100 grams of water, 45 grams of concentrated phosphoric acid, 87 grams of vanadyl sulfate, 75 grams of concentrated sulfuric acid and 760 grams of sodium aluminate. The molar ratio of the vanadium/aluminum/ phosphorous was 1/8/1. The pH of the mixture was adjusted to 7 with the addition of 50% sulfuric acid. The mixture was then filtered and the solid residue washed and dried at about 85°C. A portion of the dried material was air calcined to 540°C for six hours. The elemental analyses and physical properties of resulting vanadium aluminophosphate material were as follows:

Element, wt%	
V	3.0
Al	17.0
P	1.7
Surface Area, m ² /g	335

A further portion of the above dried material was slurried with DI water (20 g DI water per g of VAlPO_x). The pH of the slurry was adjusted to 4.0 by adding concentrated HCl solution while stirring for 15 minutes. Then the cake was filtered and washed until it was free of residual chloride. The gel was dried at 120°C for overnight and calcined in air at 538°C for 3 hours. The resulting vanadium aluminophosphate material had the properties and characteristics listed in Table 3.

Sample G

A solution was prepared by mixing 2100 grams of water, 45 grams of concentrated phosphoric acid, 87 grams of vanadyl sulfate, 75 grams of concentrated sulfuric acid and 760 grams of sodium aluminate. The molar ratio of the vanadium/aluminum/ phosphorous was 1/8/1. The pH of the mixture was adjusted to 8 with the addition of 50% solution of sulfuric acid. The elemental analyses and physical properties of the resulting vanadium aluminophosphate material were as follows:

Element, wt%	
V	2.1
Al	20.9
P	1.2
Surface Area, m ² /g	130

5

A further portion of the above dried material was exchanged four times with a 0.1N solution of ammonium nitrate to remove the excess sodium, and the resultant product was then filtered and the residue washed and dried at about 85°C. A portion of the residue was air calcined to 540°C for six hours. The resulting vanadium

10 aluminophosphate material had the properties and characteristics listed in Table 3.

The calcined acid form of each of the VAIPO_x Samples F and G were subjected to the steam deactivation test described above and the results are summarized in Table 3.

Table 3

15

	<u>VAIPO_x</u> <u>Sample F</u> <u>Invention</u>	<u>VAIPO_x</u> <u>Sample G</u> <u>Invention</u>
<u>Calcined Acid Form</u>		
V loading, wt%	3.0	2.1
Al ₂ O ₃ , wt%	39	35.6
P, wt%	1.2	0.3
Na, wt%	0.59	0.83
Surface area, m ² /g	317	304
Average pore diameter (Å)	53	36
Pore volume (>14Å), cc/g	0.42	0.27
Pore size distribution, %		
<50 Å	55	82
50-100 Å	20	10
100-150 Å	6	2
>150 Å	19	6
Steam Deactivated Catalyst (1500F for 4 hrs)		
Surface area, m ² /g	81	126

5 The results in Table 3 show that Samples F and G, with the average pore size and pore size distribution according to the invention, exhibited excellent hydrothermal stability. Sample G prepared under higher pH conditions exhibited better stability in that it maintained over 100 m²/g surface area even after severe steaming.

10 **EXAMPLE 10 - Fluid Catalytic Cracking with ZrAlPO_x**

A. Preparation of a ZrAlPO_x Material

A thermally stable, high surface area, mesoporous ZrAlPO_x material was prepared as described above in Example 1. The described wet cake of ZrAlPO_x was used for the catalyst preparations that follow.

B. Preparation of a USY/ZrAlPO_x/Clay Catalyst

15 A first catalyst, Catalyst A, was prepared using commercial Na-form USY zeolite with a silica to alumina ratio of 5.4 and a unit cell size of 24.54 Å. The Na-form USY was slurried and ball milled for 16 hours. A wet cake of the ZrAlPO_x material above was
20 slurried in deionized water, and the pH of the resultant slurry was adjusted to 4 using concentrated HCl. The ZrAlPO_x material was then filtered, washed, and ball milled for 16 hours.

A uniform physical mixture of the milled USY slurry, the milled ZrAlPO_x slurry, binding agent, and kaolin clay was prepared. The final slurry contained 21% USY, 25%
25 ZrAlPO_x, 7% binding agent, and 47% clay, on a 100% solids basis. The mixture was spray-dried to fine spherical particles with approximately 70 μ average particle diameter. The sprayed product was then air calcined, followed by ammonium exchange using an ammonium sulfate solution. The exchanged catalyst was further washed with deionized water, dried overnight, and calcined at 538°C for three hours. The properties of the final
30 catalyst are shown in Table 4.

C. Preparation of a USY/Alumina/Clay Catalyst

A second catalyst, Catalyst B, was prepared following the procedure in Example 10B, above, except that the ZrAlPO_x in Catalyst A was replaced with HCl-peptized alumina. The peptized alumina gel was prepared from pseudoboehmite alumina powder

- 5 that was peptized with HCl solution for 30 minutes (at 12 wt% solids). The properties of Catalyst B also are shown in Table 4.

D. Preparation of a USY/ZrAlPO_x/Alumina/Clay Catalyst

- A third catalyst, Catalyst C, was prepared following the procedure in Example 10B, above, except that the amount of ZrAlPO_x was reduced and part of the clay was replaced with the HCl-peptized alumina used in Example 10C so that the spray dried slurry contained 21% USY, 15% ZrAlPO_x, 25% alumina, 7% binding agent, and 32% clay, on a 100% solids basis. The final properties of Catalyst C are shown in Table 4.

E. Preparation of a USY/ZrAlPO_x/Alumina/Clay Catalyst

- A fourth catalyst, Catalyst D, was prepared following the procedure in Example 10D, above, except that the ZrAlPO_x in Catalyst C was replaced with HCl-peptized ZrAlPO_x gel, prepared by peptization of wet cake using HCl solution. The properties of Catalyst D also are shown in Table 4.

- Before evaluating the catalysts for performance on a pilot unit for catalytic cracking, each catalyst was deactivated at 1450° F and 35 psig for 20 hours using 50% steam and 50% air. The surface areas of the steamed catalysts are shown in Table 4.

TABLE 4

	Catalyst A	Catalyst B	Catalyst C	Catalyst D
Compositional Feature	25% ZrAlPO _x and No Alumina	25% Alumina and No ZrAlPO _x	15% Ball Milled ZrAlPO _x (Replaced Part of Clay) and 25% Alumina	15% Peptized ZrAlPO _x (Replaced Part of Clay) and 25% Alumina
Calcined Catalyst Properties				
Rare Earth wt. %	1.7	1.9	1.9	1.8
Na wt. %	0.1	0.1	0.1	0.1
SiO ₂ wt. %	37.1	36.7	29.6	30.3
Al ₂ O ₃ wt. %	42.5	52.0	51.6	54.2
Surface Area m ² /g	221	222	255	256
Steam Deactivated Catalyst Properties				
Surface Area m ² /g	--	123	122	120

5 F. Catalytic Cracking Process

Catalysts B through D were compared for catalytic cracking activity in a fixed-fluidized-bed ("FFB") reactor at 935°F, using a 1.0 minute catalyst contact time on a Arab Light Vacuum Gas Oil. The feedstock properties are shown in Table 5 below:

TABLE 5

Charge Stock Properties	Vacuum Gas Oil
Gravity at 60° F	0.9010
Refractive Index	1.50084
Aniline Point, ° F	164
CCR, wt. %	0.90
Hydrogen, wt. %	11.63
Sulfur, wt. %	2.8
Nitrogen, ppm	990
Basic nitrogen, ppm	250
Distillation	
IBP, ° F	536
50 wt. %, ° F	868
99.5 wt. %, ° F	1170

These catalysts were then used in the FFB pilot plant. The catalyst performances are summarized in Table 6, where product selectivity was interpolated to a constant conversion, 65 wt. % conversion of feed to 430° F material.

TABLE 6

Matrix	Catalyst B No Added ZrAlPO _x	Catalyst C + 15% Ball Milled ZrAlPO _x	Catalyst D + 15% Peptized ZrAlPO _x
Conversion, wt. %	65	65	65
Cat/Oil	3.8	3.3	3.6
C ₅ ⁺ Gasoline, wt. %	39.6	42.1	42.4
LFO, wt. %	25.4	25.6	25.5
HFO, wt. %	9.6	9.4	9.5
Coke, wt. %	5.1	5.3	5.1
RON, C ₅ ⁺ Gasoline	88.2	85.7	85.6
H ₂ S, wt. %	1.7	1.8	1.9
C ₁ + C ₂ Gas, wt. %	1.8	1.8	1.7
Total C ₃ Gas, wt. %	6.3	4.9	4.9
Total C ₄ Gas, wt. %	10.4	8.9	8.8
C ₃ ⁼ /total C ₃	0.81	0.80	0.80
C ₄ ⁼ /total C ₄	0.48	0.48	0.50
C ₄ ⁼ /C ₃ ⁼	0.98	1.10	1.13

The test results in Table 6 demonstrate that incorporation of ZrAlPO_x into the zeolite matrix resulted in significantly improved gasoline yields (as much as 2.8 wt.%). This increase in gasoline yields for Catalysts C and D resulted mostly from lower C₃ and C₄ yields. The ZrAlPO_x matrix “as-is” (Catalyst C) had a slightly higher coke-making tendency, but this tendency was alleviated by HCl peptization of the gel (Catalyst D).

The ZrAlPO_x matrix has bottoms cracking activity, and a slight decrease in HFO (heavy fuel oil) yield is observed (0.2%). The bottoms yield differences are small for these catalysts, probably because all three catalysts convert nearly all of the crackable heavy ends at this conversion level. One negative aspect of the ZrAlPO_x containing catalyst is the lower research octane number (“RON”) of the produced gasoline, lowered by as much as 2.6.

5 The ZrAlPO_x containing catalysts increased the H_2S yield by $>10\%$, suggesting that this material may have potential for SO_x removal and/or gasoline sulfur removal. The ZrAlPO_x containing catalysts increased the butylene selectivity in C_4 gas and the C_4 olefin-to- C_3 olefin ratio. The results in Table 6 clearly show that the chemistry of ZrAlPO_x is different from a typical active alumina matrix, which is usually added to improve bottoms
10 cracking.

EXAMPLE 11 - Fluid Catalytic Cracking with CeAlPO_x

A. Preparation of a CeAlPO_x Material

 A thermally stable, high surface area, mesoporous CeAlPO_x material was prepared
15 as described above in Example 2. The wet cake of CeAlPO_x described above was used for the catalyst preparations that follow.

B. Preparation of a USY/ CeAlPO_x /Clay Catalyst

 A first catalyst, Catalyst E, was prepared using commercial Na-form USY zeolite with a silica to alumina ratio of 5.4 and a unit cell size of 24.54 \AA . The Na-form USY was
20 slurried and ball milled for 16 hours. A wet cake of the CeAlPO_x material above was slurried in deionized water, and the pH of the resultant slurry was adjusted to 4 using concentrated HCl. The CeAlPO_x material was then filtered, washed, and ball milled for 16 hours.

 A uniform physical mixture of the milled USY slurry, the milled CeAlPO_x slurry,
25 binding agent, and kaolin clay was prepared. The final slurry contained 21% USY, 25% CeAlPO_x , 7% binding agent, and 47% clay, on a 100% solids basis. The mixture was spray-dried to fine spherical particles with approximately 70μ average particle diameter. The sprayed product was then air calcined, followed by ammonium exchange using an ammonium sulfate solution. The exchanged catalyst was further washed with deionized
30 water, dried overnight, and calcined at 538°C for three hours. The properties of the final catalyst are shown in Table 7.

C. Preparation of a USY/Alumina/Clay Catalyst

 A second catalyst, Catalyst F, was prepared following the procedure in Example 11B, above, except that the CeAlPO_x in Catalyst E was replaced with HCl-peptized
35 pseudoboehmite alumina. The properties of Catalyst F also are shown in Table 7.

D. Preparation of a USY/CeAlPO_x/Alumina/Clay Catalyst

A third catalyst, Catalyst G, was prepared following the procedure in Example 11B, above, except that the amount of CeAlPO_x was reduced and part of the clay was replaced with the HCl-peptized alumina used in Example 11C so that the spray dried slurry contained 21% USY, 15% CeAlPO_x, 25% alumina, 7% binding agent, and 32% clay, on a 100% solids basis HCl-peptized pseudoboehmite alumina. The final properties of Catalyst G are shown in Table 7.

E. Preparation of a USY/CeAlPO_x/Alumina/Clay Catalyst

A fourth catalyst, Catalyst H, was prepared following the procedure in Example 11D, above, except that the CeAlPO_x in Catalyst G was replaced with HCl-peptized CeAlPO_x. The properties of Catalyst H also are shown in Table 7.

Before evaluating the catalysts for performance on a pilot unit for catalytic cracking, each catalyst was deactivated at 1450° F and 35 psig for 20 hours using 50% steam and 50% air. The surface areas of the steamed catalysts are shown in Table 7.

TABLE 7

	Catalyst E	Catalyst F	Catalyst G	Catalyst H
Compositional Feature	25% CeAlPO _x and No Alumina	25% Alumina and No CeAlPO _x	15% Ball Milled CeAlPO _x (Replaced Part of Clay) and 25% Alumina	15% Peptized CeAlPO _x (Replaced Part of Clay) and 25% Alumina
Calcined Catalyst Properties				
Rare Earth wt. %	4.9	1.9	3.7	3.5
Na wt. %	0.1	0.1	0.1	0.2
SiO ₂ wt. %	38.1	36.7	31.0	30.6
Al ₂ O ₃ wt. %	46.5	52.0	57.9	55.5
Surface Area m ² /g	238	222	249	257
Steam Deactivated Catalyst Properties				
Surface Area m ² /g	90	123	130	126

F. Catalytic Cracking Process

Catalysts E and F were compared for use in a catalytic cracking process using an FFB reactor at 935°F, having a 1.0 minute catalyst contact time using Arab Light Vacuum Gas Oil. The feedstock had the properties described in Table 5 above.

- 5 The performances of the catalysts are summarized in Table 8, where product selectivity was interpolated to a constant conversion, 65 wt.% conversion of feed to 430° F material.

TABLE 8

10

	Deactivated Catalyst E	Deactivated Catalyst F
Matrix	25% CeAlPO _x	25% Activated Al ₂ O ₃
Conversion, wt. %	65	65
Cat/Oil	4.1	3.8
C ₁ + C ₂ Gas, wt. %	2.0	1.8
Total C ₃ Gas, wt. %	5.4	6.3
Total C ₄ Gas, wt. %	9.5	10.4
C ₅ ⁺ Gasoline, wt. %	40.7	39.6
LFO, wt. %	25.0	25.4
HFO, wt. %	10.0	9.6
Coke, wt. %	5.5	5.1
RON, C ₅ ⁺ Gasoline	87.6	88.2

- The results in Table 8 suggest that the CeAlPO_x matrix has bottoms cracking activity comparable to that of the activated alumina matrix. The catalysts provided comparable HFO yields. The CeAlPO_x catalyst shows higher gasoline selectivity (1.1 wt.% yield advantage).
- 15

G. Product Selectivity Improvement With Addition of CeAlPO_x

- Catalysts G and H were compared with Catalyst F to determine the benefits of adding CeAlPO_x to an FCC catalyst. An FFB reactor was used with the Arab Light Vacuum Gas Oil described above in Table 5. The performances of the catalysts are
- 20

- 5 summarized in Table 9, where product selectivity was interpolated to a constant conversion, 65 wt.% conversion of feed to 430° F material.

TABLE 9

Matrix	Catalyst F No Added CeAlPO _x	Catalyst G + 15% Ball Milled CeAlPO _x	Catalyst H + 15% Peptized CeAlPO _x
Conversion, wt. %	65	65	65
Cat/Oil	3.8	3.6	3.5
C ₅ ⁺ Gasoline, wt. %	39.6	40.7	42.0
LFO, wt. %	25.4	25.0	25.3
HFO, wt. %	9.6	10.0	9.7
Coke, wt. %	5.1	5.5	5.2
RON, C ₅ ⁺ Gasoline	88.2	87.8	85.5
H ₂ S, wt. %	1.7	1.9	1.9
C ₁ + C ₂ Gas, wt. %	1.8	1.8	1.7
Total C ₃ Gas, wt. %	6.3	5.4	5.0
Total C ₄ Gas, wt. %	10.4	9.5	9.1
C ₃ ⁼ /total C ₃	0.81	0.81	0.80
C ₄ ⁼ /total C ₄	0.48	0.52	0.49
C ₄ ⁼ /C ₃ ⁼	0.98	1.11	1.13

10

- The test results in Table 9 demonstrate that incorporation of CeAlPO_x into the matrix resulted in significantly improved gasoline yields (as much as 2.4 wt.%). The increase in gasoline yields for Catalysts G and H resulted mostly from lower C₃ and C₄ yields. The CeAlPO_x matrix "as-is" (Catalyst G) had a slightly higher coke-making tendency, but this tendency was alleviated by HCl peptization of the gel (Catalyst H).

15

The bottoms yields are comparable for all three catalysts, probably because all three catalysts convert nearly all of the crackable heavy ends at this conversion level. One negative aspect of the CeAlPO_x containing catalyst is that it lowered the research octane number ("RON") of the produced gasoline by as much as 2.7.

The CeAlPO_x containing catalysts increased the H₂S yield by >10%, suggesting that this material may have potential for SO_x removal and/or gasoline sulfur removal. The CeAlPO_x containing catalysts increased the butylene selectivity in C₄ gas, and the C₄ olefin-to-C₃ olefin ratio. The results in Table 9 clearly show that the chemistry of CeAlPO_x is different from a typical active alumina matrix, which is usually added to improve bottoms cracking.

EXAMPLE 12 - Fluid Catalytic Cracking Evaluation of CoAlPO_x and VAlPO_x

CoAlPO_x from Example 8 (Sample A) and VAlPO_x from Example 9 (Sample F) were each pelleted and sized to an average particle size of approximately 70 micrometer (μ), then steamed in a muffle furnace at 1500°F for 4 hours to simulate catalyst deactivation in an FCC unit. Ten weight percent of steamed pellets were blended with an equilibrium catalyst from an FCC unit. The equilibrium catalyst has very low metals level (120 ppm V and 60 ppm Ni).

The additives were tested for gas oil cracking activity and selectivity using an ASTM microactivity test (ASTM procedure D-3907). The vacuum gas oil feed stock properties are shown in a Table 10 below.

Table 10

<i>Charge Stock Properties</i>	<i>Vacuum Gas Oil</i>
API Gravity	26.6
Aniline Point, °F	182
CCR, wt%	0.23
Sulfur, wt%	1.05
Nitrogen, ppm	600
Basic nitrogen, ppm	310
Ni, ppm	0.32
V, ppm	0.68
Fe, ppm	9.15
Cu, ppm	0.05
Na, ppm	2.93
Distillation	
IBP, °F	358
50wt%, °F	716
99.5%, °F	1130

5

A range of conversions was scanned by varying the catalyst-to-oil ratios and reactions were run at 980°F. Gasoline range product from each material balance was analyzed with a GC equipped with a sulfur detector (AED) to determine the gasoline sulfur concentration. To reduce experimental errors in sulfur concentration associated with fluctuations in distillation cut point of the gasoline, S species ranging only from thiophene to C4-thiophenes were quantified using the sulfur detector and the sum was defined as "cut-gasoline S". The sulfur level reported for "cut-gasoline S" excludes any benzothiophene and higher boiling S species which were trapped in a gasoline sample due to distillation overlap. Performances of the catalysts are summarized in Table 11, where the product selectivity was interpolated to a constant conversion, 65wt% or 70wt% conversion of feed to 430°F₇ material.

10

15

5

Table 11

	<i>Base Case</i>	<i>+ 10% CoAlPO_x</i>	<i>+ 10% VAiPO_x</i>
Conversion, wt%	70	70	70
Cat/Oil	3.2	3.2	3.7
H ₂ yield, wt%	0.04	+0.24	+0.21
C ₁ + C ₂ Gas, wt%	1.4	+0.3	+0
Total C ₃ Gas, wt%	5.4	+0.1	-0.2
C ₃ ⁼ yield, wt%	4.6	+0	-0.1
Total C ₄ Gas, wt%	11.1	-0.2	-0.4
C ₄ ⁼ yield, wt%	5.4	-0.1	+0.1
iC ₄ yield, wt%	4.8	-0.2	-0.4
C ₅ ⁺ Gasoline, wt%	49.3	-1.7	-0.9
LFO, wt%	25.6	-0.4	+0.1
HFO, wt%	4.4	+0.4	-0.1
Coke, wt%	2.5	+1.4	+1.3
Cut Gasoline S, PPM	445	330	383
% Reduction in Cut Gasoline S	Base	26.0	13.9
% Reduction in Gasoline S, Feed Basis	Base	28.5	15.4

Data in Table 11 show that the gasoline S concentration was reduced by 26% by addition of CoAlPO_x, and 13.9% by the addition of VAiPO_x. The overall FCC yields (C₁-C₄ gas production, gasoline, LCO, and bottoms yields) changed only slightly with the CoAlPO_x and VAiPO_x addition, although some increases in H₂ and coke yields were observed. When the desulfurization results were recalculated to incorporate the gasoline-volume-loss, CoAlPO_x gave 29% S reduction and VAiPO_x gave 15% reduction.

10

5 **EXAMPLE 13 - Fluid Catalytic Cracking Evaluation of ZnAlPO_x**

ZnAlPO_x from Example 6 was pelleted and sized to an average particle size of approximately 70 micrometer (μ), then steamed in a muffle furnace at 1500°F for 4 hours to simulate catalyst deactivation in an FCC unit. Ten weight percent of steamed ZnAlPO_x pellets were blended with a steam deactivated, Super Nova D^{TR} FCC catalyst obtained from W. R. Grace. Performances of the ZnAlPO_x are summarized in Table 12.

Table 12

	<i>Base Case</i>	<i>+ 10% ZnAlPO_x</i>
Conversion, wt%	72	72
Cat/Oil	3.2	3.6
H_2 yield, wt%	0.09	+0.03
$\text{C}_1 + \text{C}_2$ Gas, wt%	1.8	+0.2
Total C_3 Gas, wt%	5.8	+0.3
$\text{C}_3^=$ yield, wt%	4.9	+0.2
Total C_4 Gas, wt%	11.3	+0.1
$\text{C}_4^=$ yield, wt%	5.9	-0.2
iC_4 yield, wt%	4.5	+0.2
C_5^+ Gasoline, wt%	50.0	-1.0
LFO, wt%	23.7	+0
HFO, wt%	4.3	-0.2
Coke, wt%	2.9	+0.4
Cut Gasoline S, PPM	477	449
% Reduction in Cut Gasoline S	Base	5.9
% Reduction in Gasoline S, Feed Basis	Base	7.7

- 5 It will be seen from Table 12 that gasoline sulfur concentration was reduced by 6% by addition of the ZnAlPO_x . The overall FCC yields (H_2 , C_1 - C_4 gas production, gasoline, LCO, and bottoms yields) changed only slightly with the ZnAlPO_x addition, although some increase in coke yield was observed. When the desulfurization results were recalculated to incorporate the gasoline-volume-loss, ZnAlPO_x gave 8% S reduction.

10

WHAT IS CLAIMED IS:

1. A process for catalytic cracking of a hydrocarbon feedstock comprising contacting the feedstock with a catalyst composition comprising a mesoporous aluminophosphate material which comprises a solid aluminophosphate composition modified with at least one element selected from zirconium, cerium, lanthanum, manganese, cobalt, zinc, and vanadium, wherein the mesoporous aluminophosphate material has a specific surface of at least $100 \text{ m}^2/\text{g}$, an average pore diameter less than or equal to 100 \AA , and a pore size distribution such that at least 50% of the pores have a pore diameter less than 100 \AA .
2. The process of claim 1 wherein the mesoporous aluminophosphate material has an average pore diameter of 30 to 100 \AA .
3. The process of claim 1 wherein the mesoporous aluminophosphate material has a specific surface area of at least $175 \text{ m}^2/\text{g}$.
4. The process of claim 1 wherein the mesoporous aluminophosphate material has a pore volume in the range from 0.10 cc/g to 0.75 cc/g .
5. The process of claim 1 wherein the catalyst composition further comprises a primary catalytically active cracking component.
6. The process of claim 5 wherein the weight ratio of the aluminophosphate material to the primary cracking catalyst component is about 0.01 to 0.5.
7. The process of claim 5 wherein the primary catalytically active cracking component comprises a large pore molecular sieve having a pore size greater than about 7 Angstrom.
8. The process of claim 7 wherein the primary catalytically active cracking component comprises a zeolite Y.

9. The process of claim 1 wherein the hydrocarbon feedstock contains sulfur and the process produces a gasoline boiling range product having a lower sulfur content than the feedstock.

ABSTRACT OF THE DISCLOSURE

A process for catalytic cracking of a hydrocarbon feedstock comprises contacting the feedstock with a catalyst composition comprising a primary cracking component, such as zeolite Y, and a mesoporous aluminophosphate material which includes a solid aluminophosphate composition modified with at least one element selected from zirconium, cerium, lanthanum, manganese, cobalt, zinc, and vanadium. The mesoporous aluminophosphate material has a specific surface area of at least 100 m²/g, an average pore size less than or equal to 100 Å, and a pore size distribution such that at least 50% of the pores have a pore diameter less than 100 Å.

Figure 1
N2 Pore Size Distribution

